



ELM[®] rHDPE-100

Recycled High Density Polyethylene

APPLICATION

Extrusion, injection moulding, blow moulding

Physical Properties	Typical Value	Method
Density (23°C)	0.94 - 0.96 g/cm ³	ISO 1183
Melt Flow Index (190°C/5 kg)	0.4 - 0.6 g/10 min	ISO 1133
Ash Content	≤ 1 %	ISO 3451
Form	3 - 5 mm granules	
Color Options	Black	

STORAGE

This product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight and heat. Inappropriate storage conditions can lead to deterioration in physical properties. It is advised to process pellets within 12 months after delivery.

PACKAGING

The product is packed in 1200 kg Big Bags.

NOTES

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests. Please contact for product samples.