

Technical Data Sheet

www.versalis.eni.com

info.polyethylene@versalis.eni.com

ERACLENE®

DB 506

HDPE

High density polyethylene

Eraclene DB 506 is a high density polyethylene resin (HDPE), hexene copolymer, obtained by gas phase technology process. The main properties of Eraclene DB 506 are emphasized when it is used for production of drip irrigation pipe.

The balanced molecular weight distribution, density and the low content of gels are successfully combined in order to provide excellent mechanical properties, sealability, melt strength and drawability at high extrusion rate.

Main Applications

Eraclene DB 506 can be easily used in blend with LLDPE and LDPE grades to modify the final properties of the drip irrigation pipe according to the specific needs.

For outdoor application, it is strongly suggested to add Anti UV. The combined usage of these additives together with Carbon Black can provide outstanding resistance to UV radiation.

Main Properties

Resin Properties

	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	0.23	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	0.9	g/10min	ISO 1133
Density	0.939	g/cm ³	ISO 1183
Melting Point	129	°C	Internal method
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	119	°C	ISO 306/A

Mechanical Properties *

	Value	Unit	Test Method
Tensile stress at yield	18	MPa	ISO 527-3
Tensile stress at break	28	MPa	ISO 527-3
Elongation at break	> 800	%	ISO 527-3
Flexural modulus	690	MPa	ISO 178
Elmendorf tear resistance MD **	20	N/mm	ISO 6383-2
Elmendorf tear resistance TD **	170	N/mm	ISO 6383-2
Hardness Shore D	58	-	ISO 868 A
ESCR ***	> 1000	h	ASTM 1693/B

(*) Values are referred to compression moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

(**) Film properties are typical of blown film extruded at 1:4.5 blow up ratio; 210°C melt temperature, die gap 1.1 mm and thickness 25 µm.

(***) 100% surface-active agent - Condition B.

Processing notes

Eraclene DB 506 is readily processable by conventional equipment. It is suggested to be used a mixing screw with a flat or slightly growing temperature profile from 190°C up to 230°C. The best balance of processing and properties of the drip irrigation pipe is obtained with a die gap between 1,5 mm and 2,5 mm.

Storage and Handling

Eraclene DB 506 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product. Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Eraclene DB 506 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.



TECHNICAL SERVICE

versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.32087
Fax +39 02 520.52052

Versalis International SA
succursale française
Port 4531 Route des Dunes - BP
59
F-59279 Mardyck

versalis S.p.A.
Via Taliercio, 14
46100 Mantova, Italia
Tel. +39 0376 305667
Fax +39 02 52043

HEADQUARTER

versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.32087
Fax +39 02 520.52052

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.