

Linear Low Density Polyethylene

LL1119F

PRODUCT DESCRIPTION

LLDPE butene resin for general packaging application.

APPLICATIONS

Product used for general packaging, including agriculture film.

TYPICAL PROPERTIES

Properties	Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)	1.0 - 1.1	g/10 min	ASTM D1238
Density	0.918 - 0.919	g/cm ³	ASTM D1505
Tensile Strength at Break	MD	Mpa	ASTM D882
	TD		
Elongation at Break	MD	%	ASTM D882
	TD		
Haze	15.0	%	ASTM D1003
Dart Drop Impact Strength, F50	115 - 125	g	ASTM D1709A

ADDITIVE

Antiblock	5500 PPM
Slip	1000 PPM
Other	NONE

DISCLAIMER: THIS TECHNICAL DATA SHEET SHOWS THE TYPICAL PROPERTIES AND THE DATA SHOWN ARE NOT TO BE CONSTRUED AS SPECIFICATIONS. THE DOCUMENT IS DESIGNED TO PROVIDE USERS GENERAL INFORMATION AND DOES NOT CONSTITUTE ANY WARRANTY OR QUALITY SPECIFICATION, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. USERS SHALL DETERMINE WHETHER THE PRODUCT IS SUITABLE FOR THEIR USE AND CAN BE USED SAFELY AND LEGALLY.