

CIPLAS by ITOCHU XLL1005

Linear Low Density Polyethylene

PRODUCT DESCRIPTION

LLDPE resin for general packaging applciation.

APPLICATIONS

Product used for general packaging, including industrial packaging.

TYPICAL PROPERTIES

Properties	Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Density	0.918 - 0.920	g/cm ³	ASTM D1505
MD	49 - 51	Мра	ASTM D882
Tensile Strength at Break TD	38 - 40		
Elengation at Brook	740 - 760	%	ASTM D882
Elongation at Break TD	980 - 1020		
Haze	14.0	%	ASTM D1003
Dart Drop Impact Strength	165 - 175	g/mil	ASTM D1709

ADDITIVE

Antiblock	6000 PPM
Slip	1200 PPM
Other	NONE