

# IMPACT PP B380G

YUPLENE B380G is a propylene impact copolymer designed for injection molding applications. YUPLENE B380G has high stiffness, excellent dimensional stability, good impact strength and has been listed by Underwriters Laboratories (UL). YUPLENE B380G is especially suitable for various electrical appliances such as washing machine parts and refrigerator parts.

## Application / Use Case

Injection / Automobile applications, Large container,  
Industrial parts for electronic

## Characteristics

High Stiffness, Impact Strength, High folw

## Specification

	Value	Unit	Test Method
Melt Index	28.0	g/10min	ASTM D1238

## Physical Properties

	Value	Unit	Test Method
IZOD Impact Strength(Notched, 23°C)	9.0	kg-cm/cm	ASTM D256
IZOD Impact Strength(Notched, -20°C)	4.5	kg-cm/cm	ASTM D256
Softening Point(Vicat)	150	°C	ASTM D1525
Tensile Strength at Yield	260	kg/cm <sup>2</sup>	ASTM D638
Elongation at Break	<300	%	ASTM D638
Flexural Modulus	12000	kg/cm <sup>2</sup>	ASTM D790

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea

Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com

www.skchem.com

ISO 9001 Certified



Hardness(Rockwell)	90	R Scale	ASTM D785
Heat Distortion Temperature	110	°C	ASTM D648
Accelerated Oven Aging(in Air at 150°C)	360	hr	ASTM D3012
Dupont Impact at -10°C	>70	kg·cm	ASTM D2794
Spiral Flow	>800	mm	SK Method

These are typical properties only, and are not to be construed as specific limits.

