

Technical Data Sheet  
**CAPILENE® G 78 TF**  
 Polypropylene Homopolymer



**Product Description**

**CAPILENE® G 78 TF** is a polypropylene homopolymer intended for extrusion applications.

<b>Features:</b>	<ul style="list-style-type: none"> <li>• High stiffness</li> <li>• Excellent transparency</li> </ul>	<ul style="list-style-type: none"> <li>• Nucleated</li> <li>• Short cycle time</li> </ul>
<b>Uses:</b>	<ul style="list-style-type: none"> <li>• Transparent trays</li> <li>• Food packaging</li> </ul>	<ul style="list-style-type: none"> <li>• Cups</li> </ul>
<b>Processing Methods:</b>	<ul style="list-style-type: none"> <li>• Extrusion</li> <li>• Thermoforming</li> </ul>	<ul style="list-style-type: none"> <li>• Injection molding</li> </ul>

Properties		Method	Typical Value*	Unit
<b>Physical</b>				
<b>Melt Flow Rate</b>	(230°C/2.16 kg)	ISO 1133	3	g/10 min
<b>Mechanical</b>				
<b>Tensile Stress at Yield</b>	(50 mm/min)	ISO 527-2	36	MPa
<b>Tensile Strain at Yield</b>	(50 mm/min)	ISO 527-2	9	%
<b>Flexural Modulus</b>	(5 mm/min)	ISO 178	1850	MPa
<b>Izod Impact Strength, notched</b>	(+23°C)	ISO 180	3.5	kJ/m <sup>2</sup>
<b>Thermal</b>				
<b>Vicat Softening Temperature</b>	(10 N)	ISO 306	156	°C
<b>Heat Deflection Temperature</b>	(0.45 MPa)	ISO 75-2	110	°C
<b>Optical</b>				
<b>Haze</b>	(1.0 mm plaque)	ASTM D1003	25	%

\*Typical values; not to be construed as specifications.

**Health, Quality, Regulations and Safety**

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel  
 Website: <http://www.Carmel-Olefins.co.il>  
 Email: [techserv@caol.co.il](mailto:techserv@caol.co.il)

**Date: June 2017**

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.