

# TURKMENPLENE TPP D30S

## POLYPROPYLENE HOMOPOLYMER FOR RAFFIA

### PRODUCT DESCRIPTION

TPP D30S is a polypropylene homopolymer with standard molecular weight distribution. The product is characterized by medium melt flow range, an optimal stabilization package and balanced physical and mechanical properties.

### APPLICATION

TPP D30S is a general purpose grade recommended for Injection Moulding, Extrusion and Thermoforming applications.

Properties	Typical Value	Method
Density (23°C)	0.902 g/cm <sup>3</sup>	ASTM D 1505
Melt Flow Index (230°C/2.16 kg)	3.5 g/10 min	ASTM D 1238
Melting Point	163°C	ASTM D 2117
Vicat Softening Point	145°C	ASTM D 1525
Heat Distortion Temperature @ 0.45 MPa	110°C	ISO 75-2
Tensile Stress at Yield	30 MPa (50mm/min)	ASTM D 638
Elongation at Yield	10 % (50mm/min)	ASTM D 638
Flexural Modulus 1% secant	1300 MPa (50mm/min)	ASTM D 638
Notched Izod Impact Strength at 23° C	2 kJ/m <sup>2</sup>	ISO 179/1eA

### STORAGE

This product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight and heat. Inappropriate storage conditions can lead to deterioration in physical properties. It is advised to process within 6 months after delivery.

### PACKAGING

The product is packed in 25 kg bags with shrink wrapped pallets.

### NOTES

These are typical properties only and are not to be construed as specifications.